



Postal Address:
 PO Box 4282
 Dandenong South, Victoria 3164
 Australia

EWFA Test Report No.	26955-00a.2	Page 1 of 2
-----------------------------	--------------------	--------------------

Report Sponsor	Issue Date
Era Polymers Pty Ltd, 25-27 Green Street, Banksmeadow, NSW 2019	7 th May 2012

Revised Test Report

This is a revision to the original test report, issued on May 7th, 2012. The revision was issued to include additional information supplied by the sponsor of the test.

Test in accordance with AS/NZS 1530.3 – 1999

Objective

To determine the performance of the material samples as described in this report when subjected to the test conditions stated in the test standard referenced below.



Product	Icynene LD-C-50
----------------	-----------------

Test Reference	Reference Date
EWFA 2695500a	21 st May 2012

Test Method	Supplementary Standards
AS/NZS 1530.3:1999 Part 3: Simultaneous determination of ignitability, flame propagation, heat release and smoke release	Nil

Product Description

The specimens tested consisted of 604mm long by 473mm wide by 94mm thick panels comprising of an expanded foam material nominated by the supplier as Icynene LD-C-50. The material had an approximate density of 10 kg m⁻³ (measured and the sponsor states a nominal density of 8 kg/m³). EWFA personnel were not involved with the selection or preparation of these test specimens. Immediately prior to conducting these tests the test specimens were conditioned to a constant mass, at a temperature of 20°C and a relative humidity of 65%.

TESTING AUTHORITY	Exova Warringtonfire Aus Pty Ltd	
	PO Box 4282 DANDENONG SOUTH VIC 3164	
	Unit 2, 409-411 Hammond Road DANDENONG VIC 3175	
	61 (0)3 9767 1000 / 61 (0)3 9767 1001	
	81 050 241 524	
	www.exova.com	
Address	Prepared By:	Reviewed By:
Phone / Fax		
ABN	J. Richardson.	P. F. Motteram
Email / Home Page		
Authorisation		

Test Results

	Mean		Standard Error
Ignition Time	Nil	minutes	Nil
Flame Propagation Time	Nil	seconds	Nil
Heat Release Integral	Nil	kJ/m ²	Nil
Smoke Release, log d	-0.2539		0.0342
Optical Density, d	0.5661	per metre	

Regulatory Indices

Ignitability Index	0	Range 0 to 20
Spread of Flame Index	0	Range 0 to 10
Heat Evolved Index	0	Range 0 to 10
Smoke Developed Index	7	Range 0 to 10

Comments

The specimens were tested on May 2nd, 2012 and none of the six specimens tested ignited.

The results only apply to the specimen mounted, as described in this report.

Each test specimen had an unattached backing of 4.5mm thick fibre reinforced cement board.

Each test specimen was restrained on the exposed faced by a layer of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal space 12mm in both directions and the assembly clamped on all sides.

Ignition is initiated by a pilot flame that is held near, but does not touch the specimen. A material that does not ignite during the standard test may ignite if contacted with a pilot flame during the test.

Conditions/Validity

This report may only be reproduced in full. Extracts or abridgements shall not be published without permission of Exova Warringtonfire Aus Pty Ltd.

These tests have been conducted in accordance with the test standard referenced above and this report should be read in conjunction with that standard.

This test report does not provide an endorsement by Exova Warringtonfire Aus Pty Ltd of the performance of the actual products supplied. The tests were performed at AWTA laboratories under the technical control of Exova Warringtonfire Aus Pty Ltd. The results of this fire test may be used to directly assess fire hazard but it should be recognized that a single test method will not provide a full assessment of fire hazard under all fire conditions.